

# Makrolon® T4006

## Preliminary Product Description\*

### Standard grades

Polycarbonate (PC), injection molding, medium viscosity, non-reinforced, For: Housing, Information technology,

Property	Test Condition	Unit	Standard	Typical Value**
----------	----------------	------	----------	-----------------

### Rheological Properties

Melt volume-flow rate (MVR)	300 °C / 1.2 kg	cm³/10 min	ISO 1133	9
-----------------------------	-----------------	------------	----------	---

### Mechanical properties (23 °C, 50 % r. F.)

Tensile modulus	1 mm/min	MPa	ISO 527-1,-2	2170
Yield stress	5 mm/min	MPa	ISO 527-1,-2	60
Yield strain	5 mm/min	%	ISO 527-1,-2	5.8
Stress at break	5 mm/min	MPa	ISO 527-1,-2	63
Strain at break	5 mm/min	%	ISO 527-1,-2	120
Izod notched impact strength	23 °C; 3 mm	kJ/m²	ISO 7391	58
Izod notched impact strength	-20 °C; 3 mm	kJ/m²	ISO 7391	48

### Thermal properties

Vicat softening temperature	50 N; 120 °C/h	°C	ISO 306	141
-----------------------------	----------------	----	---------	-----

### Processing conditions

Drying temperature	°C	120
Drying time (fresh air dryer / high speed dryer)	h	3~4

### Disclaimer

\* This is a product at a developmental stage. Further information, including amended or supplementary data on hazards associated with its use, may be compiled in the future. For this reason, no assurances are given as to type conformity, processability, long-term performance characteristics or other production or application parameters. Therefore, you use the product entirely at your own risk without having been given any warranty or guarantee and agree that we shall not be liable for any damage, of whatever nature, arising out of such use.

\*\* These values are typical values only. Unless explicitly agreed in written form, they do not constitute a binding material specification or warranted values. Values may be affected by the design of the mold/die, the processing conditions and coloring/pigmentation of the product. Unless specified to the contrary, the property values given have been established on standardized test specimens at room temperature.

The manner in which you use and the purpose to which you put and utilize our products, technical assistance and information (whether verbal, written or by way of production evaluations), including any suggested formulations and recommendations, are beyond our control. Therefore, it is imperative that you test our products, technical assistance and information to determine to your own satisfaction whether they are suitable for your intended uses and applications. This application-specific analysis must at least include testing to determine suitability from a technical as well as health, safety and environmental standpoint. Such testing has not necessarily been done by us.

Unless we otherwise agree in writing, all products are sold strictly pursuant to the terms of our standard conditions of sale which are available upon request. All information and technical assistance is given without warranty or guarantee, and is subject to change without notice. Any statement or recommendation not contained herein is unauthorized and shall not bind us. Nothing herein shall be construed as a recommendation to use any product in conflict with patents covering any material or its use. No license is implied or in fact granted under the claims of any patent. With respect to health, safety and environment precautions, the relevant Material Safety Data Sheets (MSDS) and product labels must be observed prior to working with our products.